


AMENDMENTS TO THE CLAIMS

Claim 1 (Original) A gasket rubber product made of a cured material of a fluorosilicone rubber composition containing:

100 parts by weight of an organopolysiloxane expressed by the following average composition formula:



wherein R^1 indicates a trifluoropropyl group, R^2 indicates a non-substituted or substituted monovalent aliphatic unsaturated hydrocarbon group having 2 to 8 carbon atoms, R^3 indicates a non-substituted monovalent aliphatic saturated hydrocarbon group or aromatic hydrocarbon group having 1 to 8 carbon atoms, provided that a, b and c are positive numbers satisfying $0.96 \leq a \leq 1.01$, $0.002 \leq b \leq 0.02$, $0.96 \leq c \leq 1.06$ and $1.98 \leq a + b + c \leq 2.02$;

5 to 100 parts by weight of a silica-based filler; and

a catalyst quantity of a curing catalyst.

Claim 2 (Original) A gasket rubber product according to claim 1, used in contact with a resin.

Claim 3 (Original) A gasket rubber product according to claim 2, wherein the resin is Nylon.

Claim 4 (Currently Amended) A gasket rubber product according to ~~any of claims 1 to 3~~ claim 1, wherein the compression set value at 150°C for 72 hr of a cured product of the fluorosilicone rubber composition is 10% or less and the compression set value at 150°C for 72 hr of the cured product in contact with a 6 Nylon resin is 12% or less.

Claim 5 (Currently Amended) A gasket rubber product according to ~~any of claims 1 to 4~~ claim 1, used as a resin intake manifold gasket.